



# Analysis of Russian "Vertex" High-Strength Glass Fiber

by William A. Spurgeon, Elias J. Rigas,  
and Matthew S. Burkins

ARL-TR-2045

September 1999

19991006 130

Approved for public release; distribution is unlimited.

DTIC QUALITY INSPECTED 4

**The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.**

**Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.**

**Destroy this report when it is no longer needed. Do not return it to the originator.**

# **Army Research Laboratory**

Aberdeen Proving Ground, MD 21005-5069

---

---

**ARL-TR-2045**

**September 1999**

---

## **Analysis of Russian “Vertex” High-Strength Glass Fiber**

**William A. Spurgeon, Elias J. Rigas, and Matthew S. Burkins**  
Weapons and Materials Research Directorate, ARL

---

## Abstract

---

This report presents the results of mechanical and ballistic tests required in MIL-PRF-46197A (U.S. Department of the Army, "A Laminate, High Strength Glass Fiber Reinforced Polyester Resin," U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, 16 April 1997) on Russian Vertex high-strength glass that is supposed to be equivalent to domestic S-2 glass. The results of tensile tests of 250-yield yarns of both types of fibers were very similar, with the Vertex glass possibly as much as 2% stronger. For fabricating composites, however, a pseudo-250-yield yarn made by combining three 750-yield yarns was woven to make the fabrics used in the polyester resin composites for the mechanical and ballistic tests. This pseudo-250-yield yarn was about 7% weaker than the true 250-yield yarns. The tensile strength of the composites and the ballistic performance vs. a 20-mm fragment-simulating projectile (FSP) were both below the requirements of the specification, probably as a consequence of the use of this weaker yarn. The flexure and shear properties of the composites just met the specification, while the compressive strength was about 12% low. These results suggest that the sizing needs some fine-tuning to improve the performance of the Vertex glass fibers.

## Acknowledgments

A number of people contributed to this effort. Mr. Richard O'Meara of ROM Development Corporation was instrumental in setting up the acquisition of the Vertex glass used in this project. Mr. Timothy Collins of Advanced Glass Fiber Yarns provided S-2 glass yarns for test. Mr. David Chandlee and Mr. Timothy O'Shea of the University of Delaware helped with the sample fabrication and testing the yarns. Mr. Jeffrey Swab of the Metals and Ceramics Branch of the U.S. Army Research Laboratory (ARL) performed the Weibull analyses on the tensile test results on the yarns. Mr. Donovan Harris and Mr. Phillip Patterson of the Polymers Research Branch of ARL performed the energy-dispersive x-ray analysis (EDAX) and infrared (IR) measurements, respectively. Ms. Linda Ghiorse, Mr. Paul Moy, Mr. Steven Ngyuen, and Mr. Alan Teets of the Polymers Research Branch helped set up the mechanical test equipment. Ms. Eleanor Deal, Mr. William Edmanson, and Mr. Bernard McKay of the Lethal Mechanisms Branch conducted the 20-mm fragment-simulating projectile (FSP) ballistic testing at Experimental Facility 110G. Mr. Donald Little and Mr. Vaughn Torbert of the Armor Mechanics Branch conducted the 0.22- and 0.30-cal. FSP testing at Experimental Facility 108. Ms. Mary Adamson of the ARL Foreign Intelligence Office helped obtain valuable funding for this project. These contributions are deeply appreciated.

INTENTIONALLY LEFT BLANK.

# Table of Contents

	<u>Page</u>
<b>Acknowledgments.....</b>	<b>iii</b>
<b>List of Figures .....</b>	<b>vii</b>
<b>List of Tables .....</b>	<b>ix</b>
<b>1. Introduction .....</b>	<b>1</b>
<b>2. Material Acquisition .....</b>	<b>2</b>
<b>3. Chemical Composition and Sizing Chemistry .....</b>	<b>4</b>
<b>4. Tensile Tests on Glass Yarns.....</b>	<b>6</b>
<b>5. Composite Mechanical Properties .....</b>	<b>12</b>
<b>6. Ballistic Testing .....</b>	<b>14</b>
<b>7. Conclusions .....</b>	<b>18</b>
<b>8. References .....</b>	<b>19</b>
<b>Distribution List .....</b>	<b>21</b>
<b>Report Documentation Page.....</b>	<b>37</b>

INTENTIONALLY LEFT BLANK.



## List of Figures

<u>Figure</u>	<u>Page</u>
1. A Photograph of the Vertex Glass Fabric Used in This Project.....	3
2. A Photograph of Samples of Cured, Prepregged, Vertex Glass (Right) and S-2 Glass (Left) .....	5
3. Weibull Plot of the Tensile Test Data for 250-Yield Owens-Corning S-2 Glass Yarn .....	7
4. Weibull Plot of the Tensile Test Data for 250-Yield Vertex Glass Yarn.....	8
5. Weibull Plot of the Tensile Test Data for the Pseudo-250-Yield Vertex Glass Yarn (Three Combined 750-Yield Yarns).....	10
6. Weibull Plot of the Tensile Test Data for 750-Yield S-2 Glass Yarn.....	11
7. Test Specimens for Tensile, Flexure, Compression, and Short-Beam-Shear Tests Before Testing.....	13
8. A Photograph of a 69-Ply Vertex Glass Laminate After Ballistic Testing With a 20-mm FSP .....	16

INTENTIONALLY LEFT BLANK.

## List of Tables

<u>Table</u>	<u>Page</u>
1. Tensile Test Results on S-2 and Vertex Glass Yarns.....	6
2. Required Composite Mechanical Tests.....	12
3. Results of Tensile, Flexure, Compression, and Short-Beam-Shear Tests on Vertex Glass Composites .....	13
4. Ballistic Test Results for 20-mm FSP vs. 69-Ply Vertex Glass Composite Panels .....	15
5. Ballistic Test Results of Vertex and RH Glass Composites.....	17

INTENTIONALLY LEFT BLANK.

# 1. Introduction

High-strength S-2 glass has become a very important material for structural and armor applications on military ground vehicles. This glass is significantly stronger and about seven times as expensive as the cheaper and more common fiberglass known as "E" glass. The S-2 glass has been used in the structural armor employed on the composite infantry fighting vehicle (CIFV) and more recently in the composite armored vehicle (CAV) advanced technology demonstrators. Future armored vehicles, such as Crusader, will also use substantial quantities of the S-2 glass. Its importance should increase significantly as the Army develops lighter armored vehicles that are more mobile and have better survivability features.

The only U.S. manufacturer of S-2 glass, Owens-Corning, has recently sold its S-2 glass business unit to a joint venture with a French company, Porcher.\* Owens-Corning has also sold their recently developed new glass fiber known as "Zentron," which is nominally stronger and cheaper than S-2 glass, to the same joint venture. Another French Company, Vetrotex-St. Gobain, makes a product known as RH glass that has been shown to have properties equal to those of S-2 glass [1]. However, Vetrotex-St. Gobain has been unwilling to market their RH glass in the United States. With the end of the Cold War, a Russian company, AO-Steklonit,† began to market an S-2 glass equivalent known as "Vertex HSG" outside of Russia. It has a chemical composition nominally identical to that of S-2 glass and, if properly made, should have strength and dielectric properties similar to those of S-2 or RH glass. The Vertex glass will nominally meet military requirements for type IV, class 1 S-2 glass fibers as specified in MIL-R-60346 (MR) [2]. This specification has recently been canceled, however. In any case, a more relevant question is how the glass fiber will perform in composite laminates, for which MIL-PRF-46197A [3] applies. Tests on composite panels made from the Vertex glass have not previously been conducted by an Army laboratory.

---

\* Advanced Glass Fiber Yarns, 2556 Wagener Road, Aiken, SC 29801.

† AO-Steklonit, Baschkortostan, UL Tranvainaja, 15, Ufa 450040, Russia. A U.S. representative is Mr. Richard O'Meara, ROM Development Corporation, 136 Swineburne Row, Brick Market Place, Newport, RI 02840. Mr. O'Meara was instrumental in setting up the acquisition of the Vertex glass used in this project.


This report presents results of an evaluation of the mechanical and ballistic properties of the Russian Vertex glass that was conducted to determine how well it compares to the S-2 and RH glasses in polyester resin matrix composites. The results are important; if the Vertex glass tests out well and political conditions are favorable, it could easily become an economic competitor for S-2 glass, which would lead to lower prices. An additional source of material would be desirable in view of the reluctance of Vetrotex-St. Gobain to compete in the U.S. market. History has shown that economic competition is the most reliable means of driving prices down. If the glass were to test out poorly, this will also be useful intelligence information since the glass will probably be marketed worldwide. Many potential programs depend on the quality and availability of high-strength glass fibers.

The strength properties of glass fibers and composites made from them depend, in part, on the type and manner of application of protective coatings, known as sizings, that are applied to the fibers. The sizing also controls the binding of the matrix polymer to the glass in composites. AO-Steklonit claims that their C-96 sizing performs as well as the standard Owens-Corning type-463 sizing, and that they were actually developed by the same person. The sizing should enable enough matrix resin to glass fiber bonding for good mechanical strength and still allow the composite to perform well in ballistic tests, dissipating energy from the projectile by delaminating. A simple test of the sizing was also conducted to see how well the two sizings compared.

The quality of Russian material in general is widely regarded as highly uneven. The glass purchased is supposedly the best the Russians have ever marketed.

## **2. Material Acquisition**

A total of 300 yd of 24-oz/yd<sup>2</sup> glass fabric in a 5 × 5 plain weave pattern was ordered for this project. Figure 1 shows a photograph of a piece of the fabric. This fabric style is usually made using a yarn that is sufficiently thick so that 1 lb of the yarn is 250 yd long (hence a 250-yield



**Figure 1. A Photograph of the Vertex Glass Fabric Used in This Project.**

yarn). Sufficient 250-yield yarn was fabricated by AO-Steklonit for this project. However, the amount of sizing on the fiber was deemed too great for good mechanical and ballistic results to be obtained and the 250-yield yarn was not released to the weaver. After several months, it became clear that production of additional 250-yield yarn with the desired sizing by AO-Steklonit was not likely to happen in a time frame commensurate with the requirements for this project. Accordingly, a decision was made to use an alternate approach to making the fabric with three 750-yield yarns combined into a pseudo-250-yield yarn. This process involves more handling of the glass fibers, so there is the possibility of more handling damage to the fibers. Fabrics made from these fibers could have inferior strength properties. MIL-PRF-46197A [3]

allows for the use of these fabrics with the consent of the acquiring activity. Composite Materials, Inc.,\* did the weaving. A sample of the fabric weighed  $23.8 \pm 0.1$  oz/yd<sup>2</sup>, well within the 24 oz  $\pm 3\%$  allowed by the specification.

Approximately 300 yd of the Vertex glass fabric was prepregged by Cytec-Fiberite<sup>†</sup> using CYCOM 4102 polyester resin. This resin has been used extensively by the U.S. Army Research Laboratory (ARL) for the past 15 year. MIL-PRF-46197A [3] requires a number of tests on the prepreg. The volatile content, determined by weighing small pieces of prepreg before and after a 10-minute heating to 250° F in air, was found to be  $2.10 \pm 0.3$  weight-percent, within the 0–3% allowed by the specification. Similarly, the resin content of the prepreg was determined by weighing small pieces of prepreg before and after a 2-hour heating to 1,000° F in air and subtracting the volatile content. The resin content was found to be  $34.0 \pm 0.4$  weight-percent, in excellent agreement with the  $34 \pm 3\%$  allowed by the specification. The prepregger's certificate of compliance was accepted for the other tests of the resin required in the specification. Cured composites of the prepregged Vertex glass were a little darker than similar cured composites of prepregged S-2 glass, as the photograph of the samples in Figure 2 shows.

### 3. Chemical Composition and Sizing Chemistry


The Vertex and S-2 glasses have the same chemical compositions according to vendor's literature. An energy-dispersive x-ray analysis (EDAX) was performed on the two glasses to see if there were any significant differences between them. None was found for the major metallic elements magnesium, aluminum, and silicon at about 2, 8, and 25 weight-percent, respectively. The Vertex glass did show traces (1 weight-percent or less) of potassium, calcium, titanium, and iron that did not show up in the S-2 glass. These elements, particularly potassium and calcium,

---

\* Composite Materials, Inc., 19105 63rd Ave. NE, PO Box 25, Arlington, WA 98223.

† Cytec-Fiberite, 1440 N Kraemer Blvd., Anaheim, CA 92806.





**Figure 2. A Photograph of Samples of Cured, Prepregged, Vertex Glass (Right) and S-2 Glass (Left).**

could lower the strength of the glass, although the tensile tests on the yarns would suggest that this was not a problem and the glass is just as strong as S-2 glass. The iron could account for the slight color difference noted in the composites.

Samples of both the Russian and domestic glass fibers were refluxed in methyl ethyl ketone to try to remove some of the sizing for infrared (IR) analysis. IR spectra of the extracts from the two fibers were similar but not identical. The spectra suggest that a bis-phenol-A epoxy is the major constituent of the sizings.

## 4. Tensile Tests on Glass Yarns

In order to obtain as direct a comparison between the S-2 and Vertex glass fibers as possible, tensile strength tests were run on several fiber yarns. Spools of 250-yield yarns of S-2 and Vertex glasses were obtained from Owens-Corning and Graphite Masters\* (through ROM Development Corporation), respectively. A spool of the pseudo-250-yield yarn (three 750-yield yarns combined) was also obtained from the fabric weaver, Composite Materials, Inc. Owens-Corning also provided a spool of 750-yield S-2 glass yarn that was tested to see how it compared to the 250-yield yarn.

The tensile tests were run on a standard Instron<sup>†</sup> testing machine. The gauge length of fiber was 10 in. The yarns were held in place with a special fixture. Fifty samples of each yarn were tested so that the spread in tensile strengths could be adequately explored. The results are presented in Table 1.

**Table 1. Tensile Test Results on S-2 and Vertex Glass Yarns**

Yarn	Maximum Load (lb)	Weibull Load (lb)	Weibull Slope (m)
250-Yield S-2	289 ±43	304	7.77
250-Yield Vertex	295 ±39	312	8.35
Pseudo-250-Yield Vertex	274 ±34	289	8.46
750-Yield S-2	102 ±9.3	106	13.03

In view of the spread in the data, it is clearly preferable to analyze the glass fiber tensile strength data using the methodology now generally applied to ceramic materials. This methodology is described in ASTM-C-1239-95 [4]. Weibull plots of the data for the 250-yield S-2 and Vertex glasses are shown in Figures 3 and 4. The test results for these two yarns are very

---

\* Graphite Masters, Inc., 3815 Medford St., Los Angeles, CA 90063-1900.

† Instron Corporation, 100 Royall Street, Canton, MA 02021.




Figure 3. Weibull Plot of the Tensile Test Data for 250-Yield Owens-Corning S-2 Glass Yarn.




Figure 4. Weibull Plot of the Tensile Test Data for 250-Yield Vertex Glass Yarn.

similar, with the Vertex glass marginally stronger. The results are consistent with the proposition that a single flaw population with a distribution of defect sizes determines the strength of the material.

The lines in the Weibull plots represent a fit of the data to the formula


$$P_f = 1 - \exp - (\sigma / \sigma_\theta)^m,$$


where  $P_f$  is the probability of failure,  $\sigma$  is the strength (load in this case),  $\sigma_\theta$  is the characteristic strength, and  $m$  is an experimentally determined constant. In general, the higher the "m" value, the narrower the distribution of strength-limiting flaws. The characteristic strength (load),  $\sigma_\theta$ , is the load at which 63.2% of the samples have failed. The  $m$  values for the 250-yield S-2 and Vertex glasses are quite similar, as are the characteristic strengths, 304 lb and 312 lb, respectively.

The characteristic strength of the pseudo-250-yield Vertex glass is a little lower, at 289 lb, but the  $m$  value is similar to that for the 250-yield yarn (see Figure 5). This is consistent with the possibility that the additional handling required to combine the three 750-yield yarns introduces a few extra defects in the yarn. Also, having three 750-yield yarns wound together could result in a few stress concentration points that are not present in the larger 250-yield yarn.

The 7% lower tensile strength of the pseudo-250-yield fibers indicates that this method of making a 250-yield roving should be avoided if possible.

The  $m$  value for the 750-yield S-2 glass is considerably higher than that for the heavier yarns (see Figure 6). Note too that a 250-yield yarn is not exactly three times stronger than a 750-yield yarn.





## 5. Composite Mechanical Properties

MIL-PRF-46197A [3] and its predecessor MIL-L-46197 [5] specify a number of standard mechanical tests listed in Table 2 for glass-polyester laminates.

**Table 2. Required Composite Mechanical Tests**


Test	Standard
Tensile Properties	ASTM-D638 [6]
Flexural Properties	ASTM-D790 [7]
Compression Strength	ASTM-D695 [8]
Short-Beam-Shear Strength	ASTM-D2344 [9]

These tests are to be made on specimens cut from a quasi-isotropic panel fabricated with the ply sequence  $0^\circ$ ,  $-45^\circ$ ,  $+45^\circ$ ,  $90^\circ$ ,  $0^\circ$ ,  $90^\circ$ ,  $+45^\circ$ ,  $-45^\circ$ , and  $0^\circ$ , where the angle is measured with respect to the warp direction of the fabric (the long direction of the fabric roll). This arrangement minimizes effects arising from the test specimens being cut a little off the nominal  $0^\circ$  direction of the panel. A 2-ft<sup>2</sup> panel was fabricated using plies from different rolls of the prepregged Vertex glass fabric. The individual plies were cut from regions of the prepregged fabric with minimal weft distortion (regions in which the  $0^\circ$  and  $90^\circ$  rovings were as close to perpendicular as possible). Care was taken not to introduce additional distortion into the prepregged fabric. The test specimens were cut to the required shapes by Dess Machine and Manufacturing.\* The long axis of the test specimens was the  $0^\circ$  direction of the panel. Examples of the test specimens prior to testing are shown in Figure 7. A few compression test samples were also cut in-house as 0.5-in-wide  $\times$  0.215-in-thick  $\times$  3-in-long rectangular samples. The test results on the samples and the test requirements are shown in Table 3.

---

\* Dess Machine and Manufacturing, 5049 N DuPont Hwy., Dover, DE 19901.





**Figure 7. Test Specimens for Tensile, Flexure, Compression, and Short-Beam-Shear Tests Before Testing.**

**Table 3. Results of Tensile, Flexure, Compression, and Short-Beam-Shear Tests on Vertex Glass Composites**

Test	Requirement	Vertex Glass
Tensile Strength (ksi [MPa])	43 [296]	40.4 $\pm$ 2.8 [278 $\pm$ 19]
Tensile Modulus (msi [GPa])	2.3 [15.8]	2.59 $\pm$ 0.15 [17.8 $\pm$ 1]
Compressive Strength (ksi [MPa])	20 [138]	17.6 $\pm$ 0.9 [121 $\pm$ 6.2]
Flexure Strength (ksi [MPa])	32 [221]	33.3 $\pm$ 2.2 [230 $\pm$ 15]
Flexure Modulus (msi [GPa])	2.5 [17.2]	2.55 $\pm$ 0.13 [17.6 $\pm$ 0.9]
Short-Beam-Shear Strength (ksi [MPa])	2.5 [17.2]	2.55 $\pm$ 0.1 [17.6 $\pm$ 0.7]

The tensile strength of the composite samples is 6% lower than the requirements of the specification. This is almost exactly the difference between the strength of the 250-yield and pseudo-250-yield rovings. It thus seems likely that a fabric made with the 250-yield roving would have passed this test. The tensile modulus just meets the requirements of the specification.

The flexure strength and modulus and the short-beam-shear strength just barely meet the requirements of the specification. Although these three properties depend strongly on the mechanical properties of the matrix resin and of the fiber-matrix interface, the test results would be higher if the fibers were stronger and a true 250-yield yarn had been used.

The compressive strength is well below the requirements, however. Several batches of samples were run to verify this result. A stronger and stiffer fiber would improve the compressive strength, but the difference between the 250-yield and pseudo-250-yield yarns is probably not large enough to bring the compressive strength up to the requirement of the specification. The results suggest that a modification in the sizing chemistry could improve all of the mechanical properties tested.

## **6. Ballistic Testing**

For ballistic testing, MIL-PRF-46197A [3] only requires testing of a 69-ply laminate with an areal density of  $17 \text{ lb/ft}^2$  against a 20-mm fragment-simulating projectile (FSP). The velocity at which half of the shots completely penetrate the laminate ( $V_{50}$ ) should be above 2,370 ft/s to meet the specification. It is difficult to make 69-ply laminates, and the first two large panels ( $2 \text{ ft}^2$ ) made using the prepregged Vertex glass were failures since they exhibited serious internal delaminations. At the time, it was not clear if the failure was a consequence of poor fabrication technique (as now seems probable) or if it was due to an excessive incompatibility between the resin and the sizing. In view of this, a few additional ballistic tests seemed desirable, so tests

were also run on 10-ply panels (2.3 lb/ft<sup>2</sup>) with a 0.22-cal. FSP and against a 22-ply panel (5 lb/ft<sup>2</sup>) with a 0.30-cal. FSP.

All of the ballistic laminates tested were 1 ft × 1 ft and were shot once in the center. Laminates were clamped to a metal fixture during testing using a C-clamp at each corner. A 2024 aluminum witness plate 0.020 in thick was placed behind each laminate during ballistic tests to confirm partial and complete penetrations.


Ballistic testing of the 69-ply laminate vs. a 20-mm FSP must meet or exceed 725 m/s (2,380 ft/s). The 69-ply targets had an average areal density of 17.2 lb/ft<sup>2</sup>. The results of the tests are listed in Table 4. The material came within 2% of the minimum V<sub>50</sub> of 725 m/s at the required areal density. It is probable that the glass would have passed this test if the 7% stronger 250-yield roving had been used instead of the pseudo-250-yield roving. A photograph of a panel that has been ballistically tested with the 20-mm FSP is shown in Figure 8.

**Table 4. Ballistic Test Results for 20-mm FSP vs. 69-Ply Vertex Glass Composite Panels**

Shot No.	Velocity <sup>a</sup>	Penetration	Used for V <sub>50</sub> <sup>b</sup> Calculation
1	742	Complete	N
2	765	Complete	N
3	622	Complete	Y
4	724	Complete	N
5	675	Partial	N
6	695	Partial	Y
7	708	Partial	Y
8	733	Complete	N
9	719	Complete	Y
10	713	Complete	Y
11	695	Partial	Y

<sup>a</sup> Velocity Spread: 27 m/s (88 ft/s).

<sup>b</sup> V<sub>50</sub>: 709 m/s (2,326 ft/s) ± 11 m/s (36 ft/s).



**Figure 8. A Photograph of a 69-Ply Vertex Glass Laminate After Ballistic Testing With a 20-mm FSP.**

In all cases, the ballistic test results for the Russian Vertex glass are not as good as those for the French RH glass reported in Haskell [1]. The  $V_{50}$  values are linear functions of the areal density of the armor and of the strength of the fibers. If the values are corrected to the areal densities of the RH glass and the 7% strength factor for 250-yield glass is taken into account, the Russian ballistic data come much closer to the RH data, as shown in the last column in Table 5.

The test results on all the thinner plates are presented in Table 5. The results of these tests are compared to results of previous ballistic tests on RH glass from Vetrotex-St. Gobain

**Table 5. Test Results of Vertex and RH Glass Composites**

Material	Areal Density (lb/ft <sup>2</sup> )	Projectile Caliber and Weight (Grains)	V <sub>50</sub> (m/s [ft/s])	Shots - Velocity Spread (m/s)	Normalized V <sub>50</sub> (m/s [ft/s])
Russian Vertex	2.31	0.22 (17)	472 [1,548]	4-15	494 [1,620]
RH	2.26	0.22 (17)	530 [1,740]	4-16	530 [1,740]
Russian	5.22	0.30 (44)	689 [2,260]	4-34	798 [2,617]
RH	5.65	0.30 (44)	792 [2,597]	2-38	792 [2,597]
Russian	17.19	20 mm	709 [2,326]	6-27	775 [2,541]
RH	17.55	20 mm	840 [2,755]	2-13	840 [2,755]

presented in Haskell [1]. The RH glass passed all of the tests (mechanical and ballistic) required by the specification.

## 7. Conclusions

The Russians have developed a glass fiber that comes close to meeting the requirements in MIL-PRF-96197A [3] for S-2 glass composites. The pseudo-250-yield roving used in the composites was about 7% weaker than a true 250-yield roving in direct tensile tests on the rovings. If a true 250-yield roving had been used, it is likely that the composites would have passed all of the mechanical and ballistic tests, except for compressive strength. Some modifications to the sizing are probably needed for composites of these fibers to pass this test.

Questions must also be raised about the value of MIL-PRF-96197A [3] as a specification for qualifying high-strength fibers. The specification was written for S-2 glass fibers with a special (epoxy) sizing and resin (polyester) that could be made into composites with particular mechanical and ballistic properties that were relevant to the CIFV. The same S-2 glass fiber with a different sizing (an amino silane) was used in the structural composites on the CAV in composites based on phenolic and epoxy resins. These composites have better mechanical properties than the polyester composites and are processed by cheaper vacuum-assisted resin-transfer molding techniques. New specifications for these for composites based on these resins and fibers with an amino silane sizing are needed. The new Zentron fiber also needs to be thoroughly evaluated, since it has the potential to replace S-2 glass as the high-strength glass of choice.

The future of the Russian Vertex high-strength glass is not clear. The plant where it is made has recently been temporarily closed for lack of demand. Programs in other countries could rapidly change this situation, however. The Vertex glass fiber is reasonably good and could be made even better.

## 8. References

1. Haskell, W. E. III. "High Strength Glass Second Source Qualification to Composite Armor Specification MIL-L-46197 (MR)." MTL-TR-92-30, April 1992.
2. U.S. Department of the Army. "Roving, Glass, Fibrous for Prepreg Tape and Roving, Filament Winding and Pultrusion Applications." MIL-R-60346 (MR), U.S. Army Materials Technology Laboratory, Watertown, MA, 1 June 1981 (cancelled 7 June 1997).
3. U.S. Department of the Army. "A Laminate, High Strength Glass Fiber Reinforced Polyester Resin." MIL-PRF-46197A, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, 16 April 1997.
4. American Society for Testing and Materials. "Standard Practice for Reporting Uniaxial Strength Data and Estimating Weibull Distribution Parameters for Advanced Ceramics." ASTM-C-1239-95, Philadelphia, PA, 10 September 1997.
5. U.S. Department of the Army. "A Laminate, S-2 Glass Fiber Reinforced Polyester Resin." MIL-L-46197 (MR), U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, 16 April 1997.
6. American Society for Testing and Materials. "Standard Test Method for Tensile Properties of Plastics." ASTM-D638, West Conshohocken, PA, 10 October 1997.
7. American Society for Testing and Materials. "Standard Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Insulating Materials." ASTM-D790, West Conshohocken, PA, 10 October 1997.
8. American Society for Testing and Materials. "Standard Test Method for Compressive Properties of Rigid Plastics." ASTM-D695, West Conshohocken, PA, 10 April 1996.
9. American Society for Testing and Materials. "Standard Test for Apparent Interlaminar Shear Strength of Parallel Fiber Composites by Short Beam Shear Method." ASTM-2344, 1 January 1984.

INTENTIONALLY LEFT BLANK.



<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	DEFENSE TECHNICAL INFORMATION CENTER DTIC DDA 8725 JOHN J KINGMAN RD STE 0944 FT BELVOIR VA 22060-6218
1	HQDA DAMO FDQ D SCHMIDT 400 ARMY PENTAGON WASHINGTON DC 20310-0460
1	OSD OUSD(A&T)/ODDDR&E(R) R J TREW THE PENTAGON WASHINGTON DC 20301-7100
1	DPTY CG FOR RDE HQ US ARMY MATERIEL CMD AMCRD MG CALDWELL 5001 EISENHOWER AVE ALEXANDRIA VA 22333-0001
1	INST FOR ADVNCD TCHNLGY THE UNIV OF TEXAS AT AUSTIN PO BOX 202797 AUSTIN TX 78720-2797
1	DARPA B KASPAR 3701 N FAIRFAX DR ARLINGTON VA 22203-1714
1	NAVAL SURFACE WARFARE CTR CODE B07 J PENNELLA 17320 DAHLGREN RD BLDG 1470 RM 1101 DAHLGREN VA 22448-5100
1	US MILITARY ACADEMY MATH SCI CTR OF EXCELLENCE DEPT OF MATHEMATICAL SCI MAJ M D PHILLIPS THAYER HALL WEST POINT NY 10996-1786

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DIRECTOR US ARMY RESEARCH LAB AMSRL DD J J ROCCHIO 2800 POWDER MILL RD ADELPHI MD 20783-1145
1	DIRECTOR US ARMY RESEARCH LAB AMSRL CS AS (RECORDS MGMT) 2800 POWDER MILL RD ADELPHI MD 20783-1145
3	DIRECTOR US ARMY RESEARCH LAB AMSRL CI LL 2800 POWDER MILL RD ADELPHI MD 20783-1145
	<u>ABERDEEN PROVING GROUND</u>
4	DIR USARL AMSRL CI LP (305)

NO. OF  
COPIES ORGANIZATION

1 DIR  
US ARMY RSRCH LAB  
AMSRL CP CA D SNIDER  
2800 POWDER MILL RD  
ADELPHI MD 20783

1 CDR US ARMY ARDEC  
AMSTA AR FSE  
T GORA  
PICATINNY ARSENAL NJ  
07806-5000

3 CDR US ARMY ARDEC  
AMSTA AR TD  
R PRICE  
V LINDNER  
C SPINELLI  
PICATINNY ARSENAL NJ  
07806-5000

5 PM SADARM  
SFAE GCSS SD  
COL B ELLIS  
M DEVINE  
W DEMASSI  
J PRITCHARD  
S HROWNAK  
PICATINNY ARSENAL NJ  
07806-5000

1 CDR US ARMY ARDEC  
SFAE FAS PM  
F MCLAUGHLIN  
PICATINNY ARSENAL NJ  
07806-5000

6 CDR US ARMY ARDEC  
AMSTA AR CCH  
S MUSALLI  
P CHRISTIAN  
R CARR  
M LUCIANO  
T LOUCEIRO  
PICATINNY ARSENAL NJ 07806-5000

3 CDR US ARMY ARDEC  
AMSTA AR (2 CPS)  
E FENNELL  
PICATINNY ARSENAL NJ 07806-5000

NO. OF  
COPIES ORGANIZATION

1 CDR US ARMY ARDEC  
AMSTA AR CCH P  
J LUTZ  
PICATINNY ARSENAL NJ  
07806-5000

1 CDR US ARMY ARDEC  
AMSTA AR FSF T  
C LIVECCHIA  
PICATINNY ARSENAL NJ  
07806-5000

1 CDR US ARMY ARDEC  
AMSTA AR QAC T C  
C PATEL  
PICATINNY ARSENAL NJ  
07806-5000

2 CDR US ARMY ARDEC  
AMSTA AR M  
D DEMELLA  
F DIORIO  
PICATINNY ARSENAL NJ  
07806-5000

3 CDR US ARMY ARDEC  
AMSTA AR FSA  
A WARNASH  
B MACHAK  
C CHIEFA  
PICATINNY ARSENAL NJ  
07806-5000

1 CDR WATERVLIET ARSENAL  
SMCWV QAE Q  
B VANINA  
BLDG 44  
WATERVLIET NY 12189-4050

1 CDR WATERVLIET ARSENAL  
SMCWV SPM  
T MCCLOSKEY  
BLDG 253  
WATERVLIET NY 12189-4050

NO. OF  
COPIES ORGANIZATION

8 DIR BENET LABORATORIES  
AMSTA AR CCB  
J KEANE  
J BATTAGLIA  
J VASILAKIS  
G FFIAR  
V MONTVORI  
J WRZOCIALSKI  
R HASENBEIN  
SMCAR CCB R S SOPOK  
WATERVLIET NY 12189

1 CDR WATERVLIET ARSENAL  
SMCWV QA QS  
K INSCO  
WATERVLIET NY 12189-4050

1 CDR US ARMY ARDEC  
PROD BASE MODERN ACTY  
AMSMC PBM K  
PICATINNY ARSENAL NJ  
07806-5000

1 CDR US ARMY BELVOIR RD&E CTR  
STRBE JBC  
FT BELVOIR VA 22060-5606

2 CDR US ARMY ARDEC  
AMSTA AR FSP G  
M SCHIKSNIS  
D CARLUCCI  
PICATINNY ARSENAL NJ  
07806-5000

1 US ARMY COLD REGIONS RSRCH &  
ENGR LAB  
P DUTTA  
72 LYME RD  
HANOVER NH 03755

NO. OF  
COPIES ORGANIZATION

6 US ARMY RSRCH OFC  
A CROWSON  
J CHANDRA  
J PRATER  
R SINGLETON  
G ANDERSON  
K IYER  
PO BOX 12211  
RESEARCH TRIANGLE PARK NC  
27709-2211

5 PM US TMAS  
SFAE GSSC TMA  
COL PAWLICKI  
K KIMKER  
E KOPACZ  
R ROESER  
B DORCY  
PICATINNY ARSENAL NJ  
07806-5000

1 PM TMAS  
SFAE GSSC TMA SMD  
R KOWALSKI  
PICATINNY ARSENAL NJ  
07806-5000

2 PEO FIELD ARTILLERY SYSTEMS  
SFAE FAS PM  
H GOLDMAN  
T MCWILLIAMS  
PICATINNY ARSENAL NJ  
07806-5000

2 PM CRUSADER  
G DELCOCO  
J SHIELDS  
PICATINNY ARSENAL NJ  
07806-5000

2 NASA LANGLEY RSRCH CTR  
MS 266  
AMSRL VS  
W ELBER  
F BARTLETT JR  
HAMPTON VA 23681-0001

NO. OF  
COPIES ORGANIZATION

2 CDR DARPA  
J KELLY  
B WILCOX  
3701 N FAIRFAX DR  
ARLINGTON VA 22203-1714

3 CDR DEPT OF THE AIR FORCE  
AIR FORCE RSRCH LAB  
S DONALDSON  
T BENSON TOLLE  
BLDG 654  
WRIGHT PATTERSON AFB OH  
45433-7750

1 NAVAL SURFC WARFARE CTR  
DAHLGREN DIV  
CODE G06  
DAHLGREN VA 22448

1 NAVAL RSRCH LAB  
I WOLOCK CODE 6383  
WASHINGTON DC 20375-5000

1 OFC OF NAVAL RSRCH  
MECH DIV CODE 1132SM  
Y RAJAPAKSE  
ARLINGTON VA 22217

1 NAVAL SURFC WARFARE CTR  
CRANE DIVISION  
M JOHNSON  
CODE 20H4  
LOUISVILLE KY 40214-5245

1 DAVID TAYLOR RSRCH CTR  
SHIP STRUCTURES & PROT DEPT  
J CORRADO CODE 1702  
BETHESDA MD 20084

2 DAVID TAYLOR RSRCH CTR  
R ROCKWELL  
W PHYLLAIER  
BETHESDA MD 20054-5000

1 DEFENSE NUCLEAR AGCY  
INNOVATIVE CONCEPTS DIV  
R ROHR  
6801 TELEGRAPH RD  
ALEXANDRIA VA 22310-3398

NO. OF  
COPIES ORGANIZATION

1 EXPEDITIONARY WARFARE DIV N85  
F SHOUP  
2000 NAVY PENTAGON  
WASHINGTON DC 20350-2000

1 OFC OF NAVAL RSRCH  
D SIEGEL 351  
800 N QUINCY ST  
ARLINGTON VA 22217-5660

1 NAVAL SURFC WARFARE CTR  
R HUBBARD G33 C  
DAHLGREN DIVISION  
DAHLGREN VA 2248-5000

1 NAVAL SURFC WARFARE CTR  
J H FRANCIS CODE G30  
DAHLGREN VA 22448

2 NAVAL SURFC WARFARE CTR  
CODE G32  
D WILSON  
R D COOPER  
DAHLGREN VA 22448

4 NAVAL SURFC WARFARE CTR  
CODE G33  
J FRAYSSE  
E ROWE  
T DURAN  
L DE SIMONE  
DAHLGREN VA 22448

1 CDR NAVAL SEA SYST CMD  
D LIESE  
2531 JEFFERSON DAVIS HIGHWAY  
ARLINGTON VA 22242-5160

1 NAVAL SURFC WARFARE CTR  
M E LACY CODE B02  
17320 DAHLGREN RD  
DAHLGREN VA 22448

1 NAVAL SURFC WARFARE CTR  
TECH LIBRARY CODE 323  
17320 DAHLGREN RD  
DAHLGREN VA 22448

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
4	DIR LAWRENCE LIVERMORE NATL LAB R CHRISTENSEN S DETERESA F MAGNESS M FINGER PO BOX 808 LIVERMORE CA 94550
1	LOS ALAMOS NATL LAB F ADDESSIO MS B216 PO BOX 1633 LOS ALAMOS NM 87545
1	LOS ALAMOS NATL LAB J REPPA MS F668 PO BOX 1663 LOS ALAMOS NM 87545
1	OAK RIDGE NATL LAB R M DAVIS PO BOX 2008 OAK RIDGE TN 37831-6195
3	UDLP 4800 EAST RIVER RD P JANKE MS170 T GIOVANETTI MS236 B VAN WYK MS389 MINNEAPOLIS MN 55421-1498
4	DIR SANDIA NATL LABORATORIES APPLIED MECHANICS DEPT DIV 8241 W KAWAHARA K PERANO D DAWSON P NIELAN PO BOX 969 LIVERMORE CA 94550-0096
1	BATTELLE C R HARGREAVES 505 KING AVE COLUMBUS OH 43201-2681

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	PACIFIC NORTHWEST LAB M SMITH PO BOX 999 RICHLAND WA 99352
1	LAWRENCE LIVERMORE NATL LAB M MURPHY PO BOX 808 L 282 LIVERMORE CA 94550
2	U OF DAYTON RSRCH INST R Y KIM A K ROY 300 COLLEGE PARK AVE DAYTON OH 45469-0168
1	AAI CORPORATION T G STASTNY PO BOX 126 HUNT VALLEY MD 21030-0126
1	J HEBERT PO BOX 1072 HUNT VALLEY MD 21030-0126
1	ARMTEC DEFENSE PRODUCTS S DYER 85 901 AVE 53 PO BOX 848 COACHELLA CA 92236
2	ADVNC D COMPST MATERIALS CORP P HOOD J RHODES 1525 S BUNCOMBE RD GREER SC 29651-9208
1	SAIC D DAKIN 2200 POWELL ST STE 1090 EMERYVILLE CA 94608
1	SAIC M PALMER SAIC 2109 AIR PARK RD S E ALBUQUERQUE NM 87106

NO. OF COPIES	ORGANIZATION
1	SAIC R ACEBAL SAIC 1225 JOHNSON FERRY RD STE 100 MARIETTA GA 30068
1	SAIC G CHRYSSOMALLIS SAIC 3800 W 80TH STREET STE 1090 BLOOMINGTON MN 55431
4	ALLIANT TECHSYSTEMS INC C CANDLAND R BECKER L LEE R LONG D KAMDAR G KASSUELKE 600 2ND ST NE HOPKINS MN 55343-8367
1	AMOCO PERFORM PRODUCTS INC M MICHNO JR 4500 MCGINNIS FERRY RD ALPHARETTA GA 30202-3944
1	APPLIED COMPOSITES W GRISCH 333 NORTH SIXTH ST ST CHARLES IL 60174
1	BRUNSWICK DEFENSE T HARRIS STE 410 1745 JEFFERSON DAVIS HWY ARLINGTON VA 22202
1	PROJECTILE TECHNOLOGY INC 515 GILES ST HAVRE DE GRACE MD 21078
1	CSTM ANALYTICAL ENGR SYS INC A ALEXANDER 13000 TENSOR LANE NE FLINTSTONE MD 21530

NO. OF COPIES	ORGANIZATION
1	NOESIS INC A BOUTZ 1110 N GLEBE RD STE 250 ARLINGTON VA 22201-4795
1	ARROW TECH ASSO 1233 SHELBURNE RD STE D 8 SOUTH BURLINGTON VT 05403-7700
5	AEROJET GEN CORP D PILLASCH T COULTER C FLYNN D RUBAREZUL M GREINER 1100 WEST HOLLYVALE ST AZUSA CA 91702-0296
7	CIVIL ENGR RSRCH FNDTN H BERNSTEIN C MAGNELL K ALMOND R BELLE M WILLETT E DELO B MATTES 1015 15TH ST NW STE 600 WASHINGTON DC 20005
1	NATL INST OF STAND & TECHLGY STRUCTURE & MECHANICS GRP POLYMER DIV POLYMERS RM A209 G MCKENNA GAITHERSBURG MD 20899
1	DUPONT COMPANY COMPOSITES ARAMID FIBERS S BORLESKE CHESNUT RUN PLAZA PO BOX 80702 WILMINGTON DE 19880-0702
1	GENERAL DYNAMICS LAND SYSTEMS DIV D BARTLE PO BOX 1901 WARREN MI 48090

NO. OF  
COPIES ORGANIZATION

3 HERCULES INC  
R BOE  
F POLICELLI  
J POESCH  
PO BOX 98  
MAGNA UT 84044

3 HERCULES INC  
G KUEBELER  
J VERMEYCHUK  
B MANDERVILLE JR  
HERCULES PLAZA  
WILMINGTON DE 19894

1 HEXCEL  
M SHELENDICH  
11555 DUBLIN BLVD  
PO BOX 2312  
DUBLIN CA 94568-0705

5 INST FOR ADVANCED TECH  
T KIEHNE  
H FAIR  
P SULLIVAN  
W REINECKE  
I MCNAB  
4030 2 W BRAKER LN  
AUSTIN TX 78759

1 INTEGRATED COMPOSITE TECH  
H PERKINSON JR  
PO BOX 397  
YORK NEW SALEM PA 17371-0397

1 INTERFEROMETRICS INC  
R LARRIVA  
8150 LEESBURG PIKE  
VIENNA VA 22100

1 AEROSPACE RES & DEV  
(ASRDD) CORP  
D ELDER  
PO BOX 49472  
COLORADO SPRINGS CO 80949-9472

NO. OF  
COPIES ORGANIZATION

1 PM ADVANCED CONCEPTS  
LORAL VOUGHT SYSTEMS  
J TAYLOR  
PO BOX 650003  
MS WT 21  
DALLAS TX 76265-0003

2 LORAL VOUGHT SYSTEMS  
G JACKSON  
K COOK  
1701 W MARSHALL DR  
GRAND PRAIRIE TX 75051

1 BRIGS CO  
J BACKOFEN  
2668 PETERBOROUGH ST  
HERDON VA 22071-2443

1 SOUTHWEST RSRCH INST  
ENGR & MTRL SCIENCES DIV  
J RIEGEL  
6220 CULEBRA RD  
PO DRAWER 28510  
SAN ANTONIO TX 78228-0510

1 ZERNOW TECHNICAL SERVICES  
L ZERNOW  
425 W BONITA AVE SUITE 208  
SAN DIMAS CA 91773

1 R EICHELBERGER  
409 W CATHERINE ST  
BEL AIR MD 21014-3613

1 DYNA EAST CORPORATION  
P C CHOU  
3201 ARCH ST  
PHILADELPHIA PA 19104-2711

2 MARTIN MARIETTA CORP  
P DEWAR  
L SPONAR  
230 EAST GODDARD BLVD  
KING OF PRUSSIA PA 19406

NO. OF COPIES	ORGANIZATION
2	OLIN CORPORATION FLINCHBAUGH DIV E STEINER B STEWART PO BOX 127 RED LION PA 17356
1	OLIN CORPORATION L WHITMORE 10101 9TH ST NORTH ST PETERSBURG FL 33702
1	SPARTA INC J GLATZ 9455 TOWNE CTR DRIVE SAN DIEGO CA 92121-1964
2	UNITED DEFENSE LP P PARA G THOMAS 1107 COLEMAN AVE BOX 367 SAN JOSE CA 95103
1	MARINE CORPS SYST CMD PM GROUND WPNS COL R OWEN 2083 BARNETT AVE SUITE 315 QUANTICO VA 22134-5000
1	OFC OF NAVAL RES J KELLY 800 NORTH QUINCEY ST ARLINGTON VA 22217-5000
2	NAVAL SURFC WARFARE CTR CARDEROCK DIV R CRANE CODE 2802 C WILLIAMS CODE 6553 3A LEGGETT CIR ANNAPOLIS MD 21402

NO. OF COPIES	ORGANIZATION
5	SIKORSKY H BUTTS T CARSTENSAN B KAY S GARBO J ADELMANN 6900 MAIN ST PO BOX 9729 STRATFORD CT 06601-1381
1	AMOCO POLYMERS J BANISAUKAS 4500 MCGINNIS FERRY RD ALPHARETTA GA 30005
1	HEXCEL T BITZER 11711 DUBLIN BLVD DUBLIN CA 94568
1	BOEING R BOHLMANN BOEING PO BOX 516 ,MC 5021322 ST LOUIS MO 63166-0516
1	NAVSEA OJRI G CAMPONESCHI 2351 JEFFERSON DAVIS HWY ARLINGTON VA 22242-5160
1	LOCKHEED MARTIN R FIELDS 1195 IRWIN CT WINTER SPRINGS FL 32708
1	USAF WL MLS OL A HAKIM 5225 BAILEY LOOP 243E MCCLELLAN AFB CA 55552
1	D HAMBRICK PRATT & WHITNEY 400 MAIN ST MS 114 37 EAST HARTFORD CT 06108



<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	DOUGLAS PRODUCTS DIV BOEING L J HART SMITH 3855 LAKEWOOD BLVD D800-0019 LONG BEACH CA 90846-0001
1	MIT P LAGACE 77 MASS AVE CAMBRIDGE MA 01887
1	NASA LANGLEY J MASTERS MS 389 HAMPTON VA 23662-5225
2	CYTEC FIBERITE M LIN W WEB 1440 N KRAEMER BLVD ANAHEIM CA 92806
2	BOEING ROTORCRAFT P MINGURT P HANDEL 800 B PUTNAM BLVD WALLINGFORD PA 19086
2	FAA TECH CENTER D OPLINGER AAR 431 P SHYPRYKEVICH AAR 431 ATLANTIC CITY NJ 08405
1	NASA LANGLEY RC CC POE MS 188E NEWPORT NEWS VA 23608
1	LOCKHEED MARTIN S REEVE 8650 COBB DR D73 62 MZ 0648 MARIETTA GA 30063-0648
1	WL MLBC E SHINN 2941 PST STE 1 WRIGHT PAT AFB OH 45433-7750

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	D ROSE IIT RSRCH CTR 201 MILL ST ROME NY 13440-6916
1	MATERIALS SCIENCES CORP B W ROSEN 500 OFC CENTER DR STE 250 FORT WASHINGTON PA 19034
1	DOW UT S TIDRICK 15 STERLING DR WALLINGFORD CT 06492
4	NIST R PARNAS J DUNKERS M VANLANDINGHAM D HUNSTON POLYMERS DIVISION GAITHERSBURG MD 20899
2	NORTHROP GRUMMAN ENVIRONMENTAL PROGRAMS R OSTERMAN 8900 E WASHINGTON BLVD PICO RIVERA CA 90660
1	OAK RIDGE NATL LAB A WERESZCZAK BLDG 4515 MS 6069 PO BOX 2008 OAKRIDGE TN 37831-6064
1	CDR US ARMYARDEC T SACHAR INDUSTRIAL ECOLOGY CTR BLDG 172 PICATINNY ARSENAL NJ 07806-5000
1	CDR USA ATCOM AVIATION APPLIED TECH DIR J SCHUCK M DINNING K UNSWORTH FT EUSTIS VA

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	CDR US ARMY ARDEC AMSTA AR SRE D YEE PICATINNY ARSENAL NJ 07806-5000
7	CDR US ARMY ARDEC AMSTA AR CCH B B KONRAD E RIVERA G EUSTICE S PATEL G WAGNECZ R SAYER F CHANG BLDG 65 PICATINNY ARSENAL NJ 07806-5000
1	CDR US ARMY ARDEC AMSTA AR QAC T D RIGOGLIOSO BLDG 354 M829E3 IPT PICATINNY ARSENAL NJ 07806-5000
1	CDR US ARMY ARMOR CTR ATZK MW S BLASKE FT KNOX KY 40121
1	CDR US ARMY ARDEC AMSTA AR CCH C S CHICO BLDG 65 PICATINNY ARSENAL NJ 07806-5000
1	CDR US ARMY AVCMOM AMC SMART WEAPONS MGMT OFC AMSMI SW D SAINSBURY REDSTONE ARSENAL AL 35898-5000

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	COMMANDANT US ARMY FIELD ARTILLERY CTR ATFS CD LTC BUMGARNER FT SILL OK 73503-5600
1	DIR US ARMY AVCMOM COMANCHE PRGM MGR OFC SFAE AV RAM TV D CALDWELL BLDG 5300 REDSTONE ARSENAL AL 35898
3	CDR US ARMY TACOM PM TACTICAL VEHICLES SFAE TVL SFAE TVM SFAE TVH WARREN MI 48397-5000
1	CDR US ARMY TACOM PM ABRAMS SFAE ASM AB WARREN MI 48397-5000
1	CDR US ARMY TACOM PM BFVS SFAE ASM BV WARREN MI 48397-5000
1	CDR US ARMY TACOM PM AFAS SFAE ASM AF WARREN MI 48397-500
1	CDR US ARMY TACOM PM SURV SYS FAE ASM SS T DEAN WARREN MI 48397-5000
3	CDR US ARMY SOLDIER SYST CMD NATICK RD&E CENTER SSCNC WST W NYKVIST T MERRILL S BEAUDOIN NATICK MA 01760-5018

NO. OF  
COPIES ORGANIZATION

1 GEORGIA TECH RSRCH INST  
GEORGIA INST OF TECHLGY  
P FRIEDERICH  
ATLANTA GA 30392

1 LOCKHEED MARTIN SKUNK WORKS  
D FORTNEY  
1011 LOCKHEED WAY  
PALMDALE CA 93599-2502

2 CDR NAVAL SURFC WARFARE CTR  
CADEROCK DIV  
R PETERSON CODE 2020  
M CRITCHFIELD CODE 1730 2  
BETHESDA MD 20084

2 UNITED DEFNS LTD PARTNERS  
PO BOX 359  
R BRYNSVOLD  
D MARTIN  
SANTA CLARA CA 95052-0359

2 UNITED DEFNS LTD PARTNERS  
328 W BROKAW RD  
MAIL DROP M53  
R BARRETT  
V HORVATICH  
SANTA CLARA CA 95052-0359

1 OFC OF THE SECRETARY OF DEFENSE  
JOINT CCD TEST FORCE  
OSD JCCD  
R WILLIAMS  
3909 HALLS FERRY RD  
VICKSBURG MS 29180-6199

2 GEN DYNAMICS LAND SYST  
D REES  
M PASIK  
PO BOX 2074  
WARREN MI 48090-2074

1 BATTELLE NW DOE PNNL  
T HALL  
BATTELLE BLVD  
MS K231  
RICHLAND WA 99352

NO. OF  
COPIES ORGANIZATION

2 BOEING DEFNS & SPACE GRP  
W HAMMOND  
J RUSSELL  
MS 4X55  
PO BOX 3707  
SEATTLE WA 98124-2207

1 GEN DYNAMICS LAND SYST  
MUSKEGON OPERATIONS  
W SOMMERS JR  
76 GETTY ST  
MUSKEGON MI 49442

1 CDR US ARMY ARDEC  
AMSTA AR FSP  
A P KISATSKY  
PICATINNY ARSENAL NJ  
07806-5000

1 DEPT OF THE ARMY OASARDA  
SARD SO  
DIRECTOR  
103 ARMY PENTAGON  
WASHINGTON DC 20310-0103

9 DIR  
US ARMY NATL GRND  
INTLLGNC CTR  
D LEITER  
S EITELMAN  
M HOLTUS  
M WOLFE  
S MINGLEDORF  
H C ARDLEIGH  
J A GASTON  
W P GSTATTENBAUER  
R WARNER  
220 SEVENTH ST NE  
CHARLOTTESVILLE VA 22091

1 DPTY ASSIST SECY FOR R&T  
SARD TT RM3EA79  
THE PENTAGON  
WASHINGTON DC 20301-7100

NO. OF  
COPIES ORGANIZATION

8 CDR US ARMY TACOM  
AMSTA TR R  
D THOMAS  
J BENNETT  
D HANSEN  
AMSTA JSK  
S GOODMAN  
J FLORENCE  
AMSTA TR D  
D OSTBERG  
L HINOJOSA  
B RAJU  
WARREN MI 48397-5000

3 DIR US ARMY CECOM  
NIGHT VSN & ELECT  
SENSORS DIRCTRT  
AMSEL RD NV CM CCD  
R MCLEAN  
A YINGST  
AMSEL RD NV VISP  
E JACOBS  
10221 BURBECK RD  
FT BELVOIR VA 22060-5806

2 NORTHROP GRUMMAN CORP  
ELECT SENSORS & SYST DIV  
K RADFORD  
K F SCHOCH  
1350 BEULAH RD  
PITTSBURGH PA 15235-5080

1 GRAPHITE MASTERS INC  
J WILLIS  
3815 MEDFORD ST  
LOS ANGELES CA 90063-1900

1 ROM DEV CORP  
R OMEARA  
136 SWINEBURNE ROW  
BRICK MARKET PLACE  
NEWPORT RI 02840

1 ADVANCED GLASS FIBER YARNS  
T COLLINS  
281 SPRING RUN LN  
SUITE A  
DOWNINGTON PA 19335

NO. OF  
COPIES ORGANIZATION

1 COMPOSITE MATERIALS INC  
D SHORTT  
19105 63 AVE NE  
PO BOX 25  
ARLINGTON WA 98223

1 COMPOSITE MATERIALS INC  
R HOLLAND  
11 JEWEL COURT  
ORINDA CA 94563

1 COMPOSITE MATERIALS INC  
C RILEY  
14530 S ANSON AVE  
SANTA FE SPRINGS CA 90670

2 HEXCEL  
W SWANSON  
D HARTMAN  
5794 W LAS POSITAS BLVD  
PLEASANTON CA 94588

2 COMPOSIX  
D BLAKE  
L DIXON  
120 ONEILL DR  
HEBRUN OH 43025

2 SIMULA  
J COLTMAN  
R HUYETT  
10016 S 51ST STREET  
PHOENIX AZ 85044

1 SIOUX MFG  
B KRIEL  
PO BOX 400  
FT TOTTEN ND 58335

2 PROTECTION MATERIALS INC  
M MILLER  
F CRILLEY  
14000 NW 58 CT  
MIAMI LAKES FL 33014

1 B&R SPECIALTIES INC  
J R KLINGER  
9G CENTER  
STAATSBURG NY 12580

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
2	FOSTER MILLER J J GASSNER M ROYLANCE 195 BEAR HILL RD WALTHAM MA 02354-1196
2	TEXTRON SYSTEMS R E SINGLER M FAVALORO 201 LOWELL ST WILMINGTON MA 08870-2941
1	CYTEC FIBERITE R DUNNE 1300 REVOLUTION ST HAVRE DE GRACE MD 21078
1	JPS GLASS L CARTER PO BOX 260 SLATER RD SLATER SC 29683
1	PEO GCSS SFAE GCSS W GSI M D COCHRAN WARREN MI 48397-5001
1	LTTC T J CUMMINGS CHIEF USAIC ATZB COM FT BENNING GA 31905-5800
1	PM BFV SFAE GCSS W BV S DAVIS 11 MILE RD WARREN MI 48307-5000
1	APM M1AZ PM ABRAMS MAJ K S FLYNN 6501 11 MILE RD WARREN MI 48397-5000
1	M A GILLESPIE OGARA HESS & EISENHARDT 9113 LESAINTE DR FAIRFIELD OH 45014

<u>NO. OF COPIES</u>	<u>ORGANIZATION</u>
1	APM RDT&E ABRAMS TANK SYSTEM J A GODELL SFAE GCSS W AB WARREN MI 48307-5000
1	US ARMY ARDEC AMSTA AR WEL F C T GUERRIERE INTELLIGENCE SPECIALIST PICATINNY ARSENAL NJ 07806-5000
2	CDR US ARMY TACOM AMSTA CS SF H HUTCHINSON F SCHWARZ WARREN MI 48397-5000
1	CENTRAL INTELLIGENCE AGCY OTI WDAG GT PO BOX 1925 W L WALTMAN WASHINGTON DC 20505
1	SURVIVABILITY LEAD GENERAL DYNAMICS AMPHIBIOUS SYSTEMS G WALKER 991 ANNAPOLIS WAY WOODBIDGE VA 22191
1	PMGSI HTI DIV PM SURVIVABLE SYSTEMS SFAE GCSS W GSI H M G RYZYI WARREN MI 48397-5000
1	UNITED DEFENSE LP GROUND SYST DIV M PEDRAZZI 1205 COLEMAN AVE MAIL DROP N09 SANTA CLARA CA 95052

NO. OF  
COPIES ORGANIZATION

1 SYST MGER ABRAMS  
ATZK TS  
LTC J H NUNN  
BLDG 1002 RM 110  
FT KNOX KY 40121

1 PM LIGHT TACTICAL VEHICLES  
AMSTA TR S  
MS 209  
MAJ J B MILLS  
WARREN MI 48397-5000

1 UNITED DEFENSE LP  
GROUND SYST DIV  
A P LEE  
1205 COLEMAN AVE  
MAIL DROP N11  
SANTA CLARA CA 95052

1 GROUND SYST DIV  
M MACLEAN  
1205 COLEMAN AVE  
MAIL DROP N06  
SANTA CLARA CA 95052

1 PEO GCSS  
GROUND SYST INTEGRATION  
SFAE GCSS W GSI  
R J LABATILLE  
B229  
WARREN MI 48397-5000

1 DIRCTRT OF COMBAT DEV  
C A KJORO  
320 ENGINEER LOOP  
SUITE 141  
FT LEONARD WOOD MO 65473-8929

1 CHIEF ABRAMS TESTING  
SFAE GCSS W AB QT  
T J KRASKIEWICZ  
WARREN MI 48397-5000

1 MARINE CORPS  
INTELLIGENCE ACTVTY  
D C KOSITZKE  
SUITE 250  
3300 RUSSELL RD  
QUANTICO VA 22134-5011

NO. OF  
COPIES ORGANIZATION

2 MILLIKEN RSRCH CORP  
H KUHN  
M MACLEOD  
PO BOX 1926  
SPARTANBURG SC 29303

1 CDR  
US ARMY MATERIEL COMMAND  
AMXMI INT  
5001 EISENHOWER AVE  
ALEXANDRIA VA 22333-0001

1 CDR  
NATL GRD INTELLIGENCE CTR  
IANG TMT  
220 SEVENTH ST NE  
CHARLOTTESVILLE VA 22902-5396

1 DIR  
DEFENSE INTELLIGENCE AGCY  
TA 5  
K CRELLING  
WASHINGTON DC 20310

1 CDR US ARMY ARDEC  
AMSTA AR ASF  
PICATINNY ARSENAL NJ  
07806-5000

1 CDR US ARMY TACOM  
AMSTA SF  
WARREN MI 48397-5000

1 HQDA  
DAMI FIT  
NOLAN BLDG  
WASHINGTON DC 20310-1025

1 CONNEAUGHT INDUSTRIES INC  
J P SANTOS  
PO BOX 1425  
COVENTRY RI 02816

2 BATTELLE NATICK OPERATIONS  
J P CONNORS  
B HALPIN  
209 W CENTRAL ST  
SUITE 302  
NATICK MA 01760

NO. OF  
COPIES ORGANIZATION

3 US ARMY SBCCOM  
SOLDIER SYST CTR  
J WARD  
J MACKIEWICZ  
W E HASKELL  
KANSAS ST  
NATICK MA 01760-5019

6 DIRECTOR  
US ARMY RESEARCH LAB  
AMSRL WM MB  
A ABRAHAMIAN  
M BERMAN  
A FRYDMAN  
T LI  
W MCINTOSH  
E SZYMANSKI  
2800 POWDER MILL RD  
ADELPHI MD 20783-1145

3 DIRECTOR  
US ARMY RESEARCH LAB  
AMSRL SE L  
R WEINRAUB  
J DESMOND  
D WOODBURY  
2800 POWDER MILL RD  
ADELPHI MD 20783-1145

2 DIRECTOR  
US ARMY RESEARCH LAB  
AMSRL SE R  
R CHASE  
H B WALLACE

2 DIRECTOR  
US ARMY RESEARCH LAB  
AMSRL SE DS  
R REYZER  
R ATKINSON  
2800 POWDER MILL RD  
ADELPHI MD 20783-1145

NO. OF  
COPIES ORGANIZATION

ABERDEEN PROVING GROUND

1 DIR USAMSAA  
AMXSY TD  
P DIETZ

89 DIR USARL  
AMSRL CI  
W STUREK (1121)  
AMSRL CI S  
A MARK (309)  
AMSRL CS IO FI  
M ADAMSON  
AMSRL SL B  
J SMITH  
AMSRL SL BA  
AMSRL SL BE  
D BELY (328)  
R HENRY  
AMSRL SL BG  
A YOUNG  
AMSRL WM B  
A HORST (390A)  
E SCHMIDT (390A)  
AMSRL WM BE  
G WREN (390)  
C LEVERITT (390)  
D KOOKER (390A)  
AMSRL WM BC  
P PLOSTINS (390)  
D LYON (390)  
J NEWILL (390)  
S WILKERSON (390)  
AMSRL WM BD  
R FIFER  
B FORCH  
R PIESCE-RODRIGUEZ  
B RICE  
AMSRL WM  
D VIECHNICKI (4600)  
G HAGNAUER (4600)  
J MCCAULEY (4600)  
LTC TANNER

NO. OF  
COPIES ORGANIZATION

AMSRL WM MA  
R SHUFORD (4600)  
S MCKNIGHT (4600)  
L GHIORSE  
P MOY  
S NGYUEN  
G RODRIGUEZ  
P PATTERSON  
A TEETS  
D FLANAGAN  
P TOUCHET  
D HARRIS  
AMSRL WM MB  
W DRYSDALE (390)  
J BENDER (390)  
T BLANAS (4600)  
T BOGETTI (4600)  
R BOSSOLI (120)  
L BURTON (390)  
S CORNELISON (120)  
P DEHMER (4600)  
R DOOLEY (4600)  
B FINK (4600)  
G GAZONAS (390)  
S GHIORSE (4600)  
D GRANVILLE (4600)  
D HOPKINS (390)  
C HOPPEL (390)  
D HENRY (390)  
R KASTE (390)  
M LEADORE (390)  
R LIEB (390)  
E RIGAS (4600)  
J SANDS  
D SPAGNUOLO (4600)  
W SPURGEON (4600)  
J TZENG (390)  
AMRSL WM MC  
J BEATTY  
J SWAB  
AMSRL WM MD  
W ROY (4600)  
S WALSH  
AMSRL WM T  
B BURNS  
D DIETRICH (309)

NO. OF  
COPIES ORGANIZATION

AMSRL WM TA  
W GILLICH (393)  
T HAVEL (393)  
J RUNYEON  
M BURKINS  
E HORWATH  
AMSRL WM TC  
R COATES (309)  
W DE ROSSET (309)  
AMSRL WM TD  
A GUPTA (309)  
T HADUCH  
T MOYNIHAN  
F SEITSINGER  
W BRUCHEY  
F GREGORY  
A RAJENDRAN  
D DANDEKAR  
AMSRL WM T  
A HORST  
AMSRL WM BA  
F BRANDON  
W D AMICO  
AMSRL WM BB  
J BORNSTEIN (120)  
AMSRL WM TE  
A ZIELINSKI (390)  
J POWELL (120)  
AMSRL WM BF  
J LACETERA (120)  
AMSRL SL BA  
R HENRY



REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project(0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE September 1999	3. REPORT TYPE AND DATES COVERED Final, Oct 98 - Feb 99		
4. TITLE AND SUBTITLE  Analysis of Russian "Vertex" High-Strength Glass Fiber		5. FUNDING NUMBERS  665709D650		
6. AUTHOR(S)  William A. Spurgeon, Elias J. Rigas, and Matthew S. Burkins				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)  U.S. Army Research Laboratory ATTN: AMSRL-WM-MB Aberdeen Proving Ground, MD 21005-5069		8. PERFORMING ORGANIZATION REPORT NUMBER  ARL-TR-2045		
9. SPONSORING/MONITORING AGENCY NAMES(S) AND ADDRESS(ES)		10. SPONSORING/MONITORING AGENCY REPORT NUMBER		
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT  Approved for public release; distribution is unlimited.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words)  This report presents the results of mechanical and ballistic tests required in MIL-PRF-46197A (U.S. Department of the Army, "A Laminate, High Strength Glass Fiber Reinforced Polyester Resin," U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, 16 April 1997) on Russian Vertex high-strength glass that is supposed to be equivalent to domestic S-2 glass. The results of tensile tests of 250-yield yarns of both types of fibers were very similar, with the Vertex glass possibly as much as 2% stronger. For fabricating composites, however, a pseudo-250-yield yarn made by combining three 750-yield yarns was woven to make the fabrics used in the polyester resin composites for the mechanical and ballistic tests. This pseudo-250-yield yarn was about 7% weaker than the true 250-yield yarns. The tensile strength of the composites and the ballistic performance vs. a 20-mm fragment-simulating projectile (FSP) were both below the requirements of the specification, probably as a consequence of the use of this weaker yarn. The flexure and shear properties of the composites just met the specification, while the compressive strength was about 12% low. These results suggest that the sizing needs some fine-tuning to improve the performance of the Vertex glass fibers.				
14. SUBJECT TERMS  high-strength glass fibers, high-strength fiberglass fibers, mechanical properties, ballistic properties, composites			15. NUMBER OF PAGES  42	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT  UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE  UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT  UNCLASSIFIED	20. LIMITATION OF ABSTRACT  UL	

INTENTIONALLY LEFT BLANK.

## USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number/Author ARL-TR-2045 (Spurgeon) Date of Report September 1999
2. Date Report Received \_\_\_\_\_
3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) \_\_\_\_\_  
\_\_\_\_\_  
\_\_\_\_\_
4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) \_\_\_\_\_  
\_\_\_\_\_  
\_\_\_\_\_
5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. \_\_\_\_\_  
\_\_\_\_\_  
\_\_\_\_\_
6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) \_\_\_\_\_  
\_\_\_\_\_  
\_\_\_\_\_  
\_\_\_\_\_

CURRENT  
ADDRESS

Organization

Name

E-mail Name

Street or P.O. Box No.

City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD  
ADDRESS

Organization

Name

Street or P.O. Box No.

City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)  
(DO NOT STAPLE)